

Specifications

Item	Standard	Rating
Density	ASTM E96	65lbs/cubic feet (+/- 5)
Tensile Strength	ASTM D412	265 psi
Tear Resistance	ASTM D413	Average elongation at break 1.52
Hardness	D2240	Shore A 65 +/- 5
Slip Resistance	D C1028	Coefficient of Friction .084-.090
Abrasion	D4060	2,000 cycles taber abraser 1kg, 0.329g - 0.35g loss
Flammability	ASTM E648	Critical Radiant Flux <0.10W/cm2
Chemicals	N/A	Resistant to most acids and chlorine
Volatile Organic Compounds	CDPH v1.2	<.05mg/m3

Our products contribute up to 5 POINTS in two LEED categories

- MR - Building Product Disclosure and Optimization: Environmental Product Declarations (Option 1)
- MR - Building Product Disclosure and Optimization: Environmental Production Declarations (Option 2)
- MR - Building Product Disclosure and Optimization: Sourcing of Raw Materials
- MR - Building Product Disclosure and Optimization: Material Ingredients
- EQ - Low Emitting Materials

